



SCHEDA TECNICA N°100

GRAFFIATO

Scratched-effect plastic wall coating

DESCRIPTION

GRAFFIATO is a scratched-effect plastic coating with excellent smoothing power, used for the treatment of internal and external surfaces.

The product also has good filling and masking power besides the high resistance to atmospheric agents and pollutants.

GRAFFIATO prevents from cracks and detachments, and is available in three different granulometries: coarse, medium or fine grit.

APPLICATION

New Walls:

- The surface to be treated must be dry. Conditions and thickness of the plaster layer affect the drying and hardening time, so make sure it has at least 28 days of curing time.
- The substrate has to be well prepared and suitable for coating: dry plaster, not any granules from plaster.
- Level out imperfections of the internal support with RASAN STUCCO or with K-STUCCO; use instead RIVENDUIT CALCE for the external support . In case of holes or micro-cracks, fill the inner walls with STUCCO TRE STELLE and the external ones with ESTERN STUCCO.
- Use the sandpaper in order to remove surface irregularities and then eliminate dust deposits.
- Apply 1 coat of SCIK PURAL ACRIL insulation or FISSATIVO ACRILICO TRE STELLE.
- Apply the special SOTTOFONDO PER RIVESTIMENTI .
- Proceed applying with spatula, a coat of GRAFFIATO, ready to use.

Old Walls:

- The surface to be treated must be dry.
- Scrape off any loose flaking and poorly adhering coating, scraping and washing the surface with plenty of water or using a pressure washer.
- Proceed following the instruction of 'NEW WALL' from the third point onwards.



COLORIFICIO RIVEDIL di COSIMO CODARDO

Via Prov.le per Veglie Km 0,500 - 73015 Salice Salentino (Le) Italy

Tel. (+39) 0832 731293 - (+39) 0832 731273


P.IVA 01122590753

www.rivedil.com - export@rivedil.com

TECHNICAL DATA

Nature of the bond	Acrylic copolymer in aqueous emulsion
Viscosity	
Drying Time	2 h at touch, 12-24 h complete.
Thinning	Ready to use
Yield	grana grossa@3,200-3,500@grana media@2,800-3,000@grana fine@2,00-2,500m ² /Kg
Specific weight	N/A
Colors	'Scratched' folder
Dry aspect	Scratched/ matt
Wet aspect	
Storing	Max Temp. +30°C, Min T. +5°C
Stability	2 years (in sealed, unopened original packing)
VOC	µGr/m ³
TVOC	N/A
PH	N/A
Cleaning	Water
Packing	25KG,10KG

CHARACTERISTICS

Characteristics:	Linea Rivestimenti.
Can be applied on:	Walls,Wood.
for:	Ineterni ed Exteriors.
Certifications:	

TOOLS AND RELATED PRODUCTS

Tools:	Spalter.
Related products:	RASAN STUCCO,K-STUCC,K,RIVENDUIT CALCE,STUCCO TRE STELLE,ESTERN STUCCO,SCI K PURAL ACRIL,FISSATIVO TRE STELLE,SOTTOFONDO PER RIVESTIMENTI.

SAFETY INSTRUCTIONS

The product does not require labelling under the Decree 285 of 16/7/98 and subsequent amendments and updates. Use the product in accordance with the relevant health and safety regulations of the country. Do not dispose of the containers in the environment after use; let the residues dry and treat them as special waste. For further information please refer to **SSR100** safety data sheet.

ITEM SPECIFICATION:

Scratched-effect plastic wall coating. Applications to be made on already prepared surfaces of scratched-effect plastic wall coating for internal and external. GRAFFIATO cod.GRF01, determined in quantities by the substrate absorption.

Supply and installation of material € per sqm.

NOTES

- Please note that due to technical reasons caused by the tinting of the product the indicated Specific Weight of the product may differ from the Package Net Weight.
- In the original, sealed containers and in appropriate temperature conditions . The period of stability is purely indicative, and refers to the minimum stability period of the product if stored ideal conditions according to the instructions provided. If properly stored the products stability period may extend several years.
- Rivedil ensures that the information herein is provided to the best of its experience and its technical and scientific knowledge , however , being elements such as weather conditions, labor , tools, quality of third party products and others, not under the direct control of the Rivedil , this document does not constitute a warranty , nor does Rivedil authorize its agents and / or representatives to provide any kind of warranty based on the information contained in this document . We recommend that you always check the suitability of the product to each specific instance . This supersedes all previous editions.

colorificio
Rivedil
made in Italy

COLORIFICIO RIVEDIL di COSIMO CODARDO

Via Prov.le per Veglie Km 0,500 - 73015 Salice Salentino (Le) Italy

Tel. (+39) 0832 731293 - (+39) 0832 731273

P.IVA 01122590753

www.rivedil.com - export@rivedil.com